



CHEMICAL RESISTANCE DATA SHEET

	TEST TEMP. °C	GreenTEC Pro Carbon	GreenTEC Pr	GreenTEC	PLA INX1	PLA INX2	PETG	XPETG	DuraPro ABS	DuraPro ASA	TPU FLEX	PEARL	FLAX	WOOD	BioFusion
ACETONE	20	●	●	●	●	●	●	●	●	●	○	●	●	●	●
MEK, METHYLETHYLKETON	20	-	-	-	-	-	-	-	-	-	○	-	-	-	-
AMMONIA, 10% WATER	20	-	-	-	-	-	-	-	-	-	●	-	-	-	-
AMMONIUM NITRATE (FERTILIZER)	20	-	-	-	-	-	-	-	-	-	●	-	-	-	-
ASTM OIL NO. 1	80	-	-	-	-	-	-	-	-	-	●	-	-	-	-
ASTM OIL NO. 2	80	-	-	-	-	-	-	-	-	-	●	-	-	-	-
ASTM OIL NO. 3	80	-	-	-	-	-	-	-	-	-	●	-	-	-	-
NORMAL PETROL	20	-	-	-	-	-	-	-	-	-	●	-	-	-	-
PREMIUM GASOLINE	20	-	-	-	-	-	-	-	-	-	●	-	-	-	-
BITUMEN / ASPHALT	80	-	-	-	-	-	-	-	-	-	●	-	-	-	-
BRAKE FLUID	80	-	-	-	-	-	-	-	-	-	●	-	-	-	-
CYCLOHEXANE	20	-	-	-	-	-	-	-	-	-	●	-	-	-	-
MINERAL OIL	20	●	●	●	●	●	-	-	●	●	○	●	●	●	●
DIMETHYLFORMAMIDE	20	-	-	-	-	-	-	-	-	-	○	-	-	-	-
ETHYL ACETATE	20	-	-	-	-	-	-	-	-	-	○	-	-	-	-
ETHYL ALCOHOL [10%]	20	●	●	●	●	●	●	●	●	●	●	●	●	●	●
ETHYL ALCOHOL [95%]	20	○	○	○	○	○	○	○	-	-	○	○	○	○	○
FRIGEN R11	20	-	-	-	-	-	-	-	-	-	●	-	-	-	-
DIETHYLENE GLYCOL	20	-	-	-	-	-	-	-	-	-	●	-	-	-	-
ISOPROPYL ALCOHOL	20	-	-	-	-	-	-	-	-	-	●	-	-	-	-
LIMESCALE	20	-	-	-	-	-	-	-	-	-	●	-	-	-	-
METHANOL	20	-	-	-	-	-	-	-	-	-	○	-	-	-	-
METHYL CHLORIDE	20	-	-	-	-	-	-	-	-	-	○	-	-	-	-
TRICHLOROETHANE	20	-	-	-	-	-	-	-	-	-	○	-	-	-	-
CHLOROFORM	20	○	○	○	○	○	-	-	-	-	-	○	○	○	○
1,2 DICHLORETHANE	20	○	○	○	○	○	-	-	-	-	-	○	○	○	○
ENGINE OIL	80	-	-	-	-	-	-	-	-	-	●	-	-	-	-
SODIUM CHLORIDE, AQUATIC 10%	20	-	-	-	-	-	-	-	●	●	●	-	-	-	-
PHOSPHORIC ACID, AQUATIC 10%	20	-	-	-	-	-	-	-	●	●	○	-	-	-	-
POTASSIUM SOAP GREASE	80	-	-	-	-	-	●	●	●	●	●	-	-	-	-
LITHIUM SOAP GREASE	80	-	-	-	-	-	●	●	●	●	○	-	-	-	-
SODIUM SOAP GREASE	80	-	-	-	-	-	●	●	●	●	●	-	-	-	-
HYDROCHLORIC ACID [1.5%]	20	○	○	○	○	○	-	-	●	●	-	○	○	○	○
HYDROCHLORIC ACID [10%]	20	-	-	-	-	-	-	-	-	-	○	-	-	-	-
SULFURIC ACID [2,5%]	20	○	○	○	○	○	-	-	-	-	-	○	○	○	○
SULFURIC ACID [10%]	20	-	-	-	-	-	-	-	-	-	●	-	-	-	-
Tetrahydrofuran (THF)	20	○	○	○	○	○	-	-	-	-	○	○	○	○	○
WATER DISTILLED	20	●	●	●	●	●	●	●	●	●	●	●	●	●	●
WATER DISTILLED	50	●	●	●	●	●	●	●	●	●	●	●	●	●	●
WATER DISTILLED	80	●	●	●	●	●	●	●	●	●	●	●	●	●	●
ACETIC ACID	20	●	●	●	●	●	-	-	-	-	-	●	●	●	●
GLYCERIN	20	●	●	●	●	●	-	-	-	-	-	●	●	●	●
CAUSTIC SODA [10%]	20	○	○	○	○	○	-	-	-	-	-	○	○	○	○
NITRIC ACID [3.5%]	20	○	○	○	○	○	-	-	-	-	-	○	○	○	○
...	...	-	-	-	-	-	-	-	-	-	-	-	-	-	-

● resistant ● conditionally resistant ○ unstable ○ very unstable ○ soluble - none specification

FURTHER INFORMATION

The information provided is based on our current knowledge and experience. A legal however, binding assurance of certain properties can not be derived. For application, use, processing or other use of this information or products as well, Extrudr assumes no liability for the resulting consequences. The buyer takes over the full responsibility for the application, use and processing of the products and use of the information as well as for all consequences. Extrudr assumes no liability for any violations regarding any patent, copyright or other rights of owned or administered by third parties application, use and processing of the products and use of the information by the buyers.